



CHEMISCH-TECHNISCHE-  
PRODUKTE

**SCH**  
schachermayer

# INFORMATION

## DOBA VYTVRDENIA

| teplota kotevného podkladu | doba spracovania<br>FIS SB | doba vytvrdenia<br>FIS SB |
|----------------------------|----------------------------|---------------------------|
| - 14°C – - 10°C            | 60Min.                     | 36h                       |
| - 9°C – - 5°C              | 30Min.                     | 24h                       |
| - 4°C – ±0°C               | 20Min.                     | 8 h                       |
| + 1°C – + 5°C              | 13Min.                     | 4 h                       |
| + 6°C – +10°C              | 9 Min.                     | 120Min.                   |
| + 11°C – +20°C             | 5 Min.                     | 60Min.                    |
| + 21°C – +30°C             | 4 Min.                     | 45Min.                    |
| + 31°C – +40°C             | 2 Min.                     | 30Min.                    |